



FOODLUBE SPRAY

**Food grade multipurpose lubricant spray.
Non-toxic, water displacing, lubricating, penetrating lubricant with good corrosion protection. Ideal for use in food/clean environments.**

FEATURES

- Temperature range –20⁰C to 110⁰C
- Good load carrying properties (180 kg weld load)
- Good dewatering properties
- Excellent penetration
- Thin long lasting fillm
- Excellent corrosion protection
- Does not contain: mineral hydrocarbons, animal derived materials, nut oils or genetically modified ingredients.
- FDA Group 21 CFR 178.3570
- NSF H1 registered – 121616
- DIN V 10517

DIRECTIONS FOR USE

- Shake well before use and spray from a distance of 15-25 cm.

Technical and Safety Data Sheets are available from:

Fax Back Facility : +44 (0)113 232 2770
Web Site : www.rocol.com
Customer Service : +44 (0)113 232 2700

Issue 1571c: 20/06/02

1

ROCOL Lubricants

ROCOL House, Swillington, Leeds LS26 8BS, England.

Tel: +44 (0)113 232 2600 Fax: +44 (0)113 232 2760

www.rocol.com

www.rocolshop.com

ROCOL is a BS EN ISO 9001 registered company.

ROCOL is a trade mark of ITW Inc.

The information in this publication is based on our experience and reports from customers. There are many factors outside our control or knowledge which affect the use and performance of our products, for which reason it is given without responsibility.

TECHNICAL DATA



FOODLUBE SPRAY

TECHNICAL DATA (typical values)

Appearance	Thin oily film
Base type	Blend of esters
Solvent	None
Propellant	CO ₂
Temperature range	-20 ⁰ C to 110 ⁰ C
Base fluid viscosity at 40 ⁰ C	8 cSt
Shell 4 ball (IP 239)(ASTM D2596)	
Weld load	180 kg
Storage	Storage temperature should be kept below 50 °C. Storage area should be: out of direct sunlight.
Pack sizes	300 ml

Issue 1571c: 20/06/02

2

ROCOL Lubricants

ROCOL House, Swillington, Leeds LS26 8BS, England.

Tel: +44 (0)113 232 2600 Fax: +44 (0)113 232 2760

www.rocol.com

www.rocolshop.com

ROCOL is a BS EN ISO 9001 registered company.

ROCOL is a trade mark of ITW Inc.

The information in this publication is based on our experience and reports from customers. There are many factors outside our control or knowledge which affect the use and performance of our products, for which reason it is given without responsibility.

TECHNICAL DATA