



Chemical resistance guide for Vyflex

*Please refer to the Performance level chart for interpretation of codes given in the table.

It is important to note that the performance of these gloves may be different if mixtures of chemicals are involved.

Chemical	Performance Level
Acetonitrile	0
Ammonia 35%	1
Ethylene glycol	6
Isopropyl alcohol	3
Methanol	1
Methyl t-butyl ether	1
n-heptane	2
Sodium hydroxide 50%	6
Sodium hypochlorite 13%	6
Sulphuric acid 96%	4
Tetrachloroethylene	1
Xylene	1

*Performance Level chart

Performance Level	1	2	3	4	5	6
Breakthrough time (min)	>10	>30	>60	>120	>240	>480

The information contained here is advisory and is intended to guide and inform only. This information is based on the view on BM Polyco Ltd in light of all available data and is not subject to any guarantee on our part regarding the performance of a particular glove style. As it is impossible to test every situation encountered and all chemical and mixtures of chemicals, the user is advised to test the particular glove style before and periodically during use.